

	Formex GK	Formex GL	Formex GS	Formex EP	Formex N3	Formex GN	Formex TCI
材質 厚み	PP 単層 0.127 ~ 1.57mm	PP 単層 0.25/ 0.43mm	PP 単層 0.25 ~ 0.76mm	PP 単層 0.25 ~ 1.57mm	PC 三層 0.20/ 0,25mm	PP 単層 0.25 ~ 1.57mm	PP 単層 0.25/ 0.50mm
RTI	115°C	125°C	115°C	110°C	130°C	115°C	115°C
CTI	0/600V	0/600V	0/600V	0/600V	3/175V	0/600V	0/600V
吸水率	0.06%	0.06%	0.06%	0.06%	0.20%	1.70%	-
比重	1.035	0.972	1.035	0.972	1.21	1.14	-
絶縁耐圧 V at 10 mil	16,264V	18,799V	16,830V	16,512V	17,587V	9,000V, Hi- PotAC5KV /60s/10mA	10,000V
張力強度 機械/直角 方向	308/224 Kg/Cm2	350/203 Kg/Cm2	308/224 Kg/Cm2	259/224 Kg/Cm2	504/483 Kg/Cm2	308/224 Kg/Cm2	168/98 Kg/Cm2